

Super-Bond C&B et Panavia F 2,0 et Relyx X Unicem

microTBS (traction en MPA)

	dentine superficielle	dentine profonde	dentine cervicale
Super-Bond C&B	31	18	24
Panavia F 2,0	29	10	10
Rely X Unicem	8	6	6

extrait de :

"micro tensile bond strength of 3 luting resins to human regional dentine"

B.Yang Université de Kiel , Allemagne

in Dental Materials (2006) 22,45-56